

EMAPOXY ZINC PHOSPHATE PRIMER

PRODUCT DESCRIPTION

Emirates Emapoxy Zinc Phosphate Primer is a two-component polyamide-cured epoxy resin-based primer, engineered to be pigmented with zinc phosphate.

PRODUCT FEATURES

- Enhanced with anti-corrosive properties
- Abrasion resistant
- Water resistant
- Chemicals resistant

RECOMMENDED USE

This industrial product is recommended for application as a primer for corrosive environments, steel structures, equipment and pipe work.

TECHNICAL SPECIFICATIONS

Color	Grey, Red
Finish	Matt
Spreading Rate	8.6 - 13 m ² / litre
Volume Solids (ASTM d2697)	52 ± 2%
Specific Gravity	1.55 ± 0.05
Dry Film Thickness	40 - 60 Microns / Coat
Wet Film Thickness	75 - 115 Microns / Coat
Packaging Size	3.6L + 18L
Flash Point	25° C



EMAPOXY ZINC PHOSPHATE PRIMER

APPLICATION DATA

Application Method	Brush, Roller, Spray
Thinner	5 - 10% Emirates Epoxy Thinner depending on the application method
Airless Spray Requirements	Nozzle Size: 0.018" – 0.020" Pressure: 2200 psi
Mixing Ratio by Volume	(4:1) (Base:Hardener)
Pot Life @30° C	8 hours

SURFACE PREPARATION

The surface must be clean, dry and free from oil, grease, dust and loose particles prior to application.

DRY TIME

Touch Dry	6 hours
Dry to Recoat	30 hours
Full Dry	30 hours - 7 days

*Based on temperatures at 30 degrees Celsius.

*Humidity, air movement, film thickness and number of coats may impact dry time.

RECOMMENDED SYSTEM

Emirates Emapoxy Zinc Phosphate Primer	50 Microns
Emirates Emapoxy Undercoat	125 Microns
Emirates Ema Pu Topcoat	50 Microns



EMAPOXY ZINC PHOSPHATE PRIMER

HEALTH & SAFETY

Oil-based (solvent-based) paints require extra precautions due to their fumes and flammability. We highly recommend following your local safety regulations. Ensure you are working in a well-ventilated space to reduce the inhalation of harmful vapors and wear a suitable respirator mask when painting in enclosed areas. To avoid skin and eye contact, always wear protective gear such as solvent-resistant gloves and goggles. In case of skin contact, wash thoroughly with soap and water. If the paint gets into your eyes or is accidentally ingested, seek medical attention immediately. Please keep paints and solvents out of the reach of children and pets.

STORAGE & HANDLING

We highly recommend storing our paints in proper storage conditions as per your local regulations. Keep the paint container tightly sealed and away from direct sunlight and extreme temperatures. Ensure oil-based paints are stored away from any ignition sources, such as heat, sparks, or open flames, due to their flammability. Do not return unused paint to the original container to prevent contamination. For disposal, follow local hazardous waste protocols. Avoid washing brushes or spills down drains, as these paints require special disposal. Handle with care and mix thoroughly before use

SHELF LIFE

*For best results, please use within 18 months of the production date.

*Shelf life can be highly affected by storage conditions, in particular, the method of sealing the container.

DISCLAIMER

The data provided is based on our present state of knowledge and is intended to provide general information about our product and its uses. Emirates Paints will not be responsible for any claims after the product had been used without proper testing. Any existing industrial property rights must be observed. The quality of our product is guaranteed under our general conditions of sales.

